

Elastopack 201

2-component, phthalate free, hydrophobic, flexible polyurethane grout for sealing dry to moist cracks and joints with a non-expanding grout in concrete and masonry structures. Elastopack 201 can be injected or poured.



• field of application

- Sealing of moving or non-moving cracks in concrete or masonry structures.
- Sealing of dry to moist cracks in concrete or masonry structures.
- Sealing of hairline cracks where other resins cannot penetrate.
- Filling of voids which can be subject to movement.
- Filling of joints between horizontal concrete slabs by pouring or pumping.

• advantages

- ADR free transport.
- Phthalate free resin, REACH compliant.
- Packed as a complete pre-weighted set.
- Solvent free.
- Non-flammable.
- Good flexibility.
- Low viscosity, fast and deep penetration.
- User friendly: Easy to use 2/1 volumetric mixing ratio, used as 1-component product after mixing.
- Cured resin has a very good all-round chemical resistance^(*).

• description

Elastopack 201 is a 2-component, phthalate free, injection grout consisting of a resin and a hardener, which are injected as 1-component system after mixing. After curing, the grout will become a dense and elastic material.

Elastopack is packed in pre-weighted sets composed of:

- A-component : polyol blend.
- B-component : di-isocyanate hardener.
- Mixing ratio A/B : 2/1 volumetric.

• application

1. Preparation

- To improve adhesion of the resin to the surface, the surface needs to be sound, clean and free from dust, debris, grease, oils and laitance.
- Low temperature conditions will significantly increase the viscosity and the reaction time of the products. To minimize this effect, store the product at room temperature for a minimum of 24 hours before use.
- Add the complete contents of the A-component to the B-component. Mix thoroughly with a mechanical mixer at moderate speed (500 rpm). Shake A-component thoroughly before adding to B-component.
- Do not pre-mix more material than can be used within the pot life of the product.

2. Injection

- The product is used as a 1-component product after pre-mixing in a 2/1 volumetric ratio.
- The product can be injected or poured into the joint, void or crack to be filled as a 1-component system. Standard 1-component hand pumps or electrical airless diaphragm pumps can be used.
- All pumps and equipment should be cleaned immediately after use with Washing Agent Eco to prevent the material from gelling or curing inside the injection equipment.

• technical data/properties

Property	Value		Norm
	Component A	Component B	
Solids	100%	100%	EN ISO 3251
Viscosity at 25°C (mPas)	Approx. 130	Approx. 150	EN ISO 3219
Density (kg/dm ³)	Approx. 0,975	Approx. 1,230	EN ISO 2811
Flash Point (°C)	> 140	> 160	EN ISO 2719
Mixed product			
Mix viscosity (mPas) • at 8°C • at 25°C	Approx. 435 Approx. 160		EN ISO 3219
Pot life (min) • at 8°C • at 25°C	Approx. 120' Approx. 45'		EN ISO 9514
Cured			
Tensile strength (MPa)	Approx. 3,5		EN ISO 527
Elongation	Approx. 115 %		EN ISO 527
Adhesion to dry concrete (MPa)	Approx. 3,1		EN 1542
Hardness Shore A	Approx. 65		EN ISO/R868

^(*) Typical values - all tests were made under conditioned temperature of 21°C.

• appearance

A-component : yellow transparent liquid.
B-component : dark brown liquid.

• consumption

Has to be estimated by the engineer or operator and depends on width and depth of the cracks and voids, which need to be filled.

• packaging

3 l set

A-component: 2 l plastic pail in cardboard box.
B-component: 1 l metal drum in cardboard box.
1 box = 5 x 2 l A-component.
1 box = 10 x 1 l B-component.

1 pallet

18 boxes A-component.
9 boxes B-component.
Total 90 sets (270 l).

15 l set

A-component: 10 l plastic jerry can.
B-component: 5 l metal drum.

1 pallet

30 x 10 l A-component.
30 x 5 l B-component.
Total 30 sets (450 l).

• storage	Elastopack 201 should be stored in a dry area, free from ground. Storage temperature must be between 5°C and 30°C. Once the packaging has been opened, the useful life of the material is greatly reduced and should be used as soon as possible. Shelf life: 2 years
• accessoires	<u>To be purchased separately</u> <ul style="list-style-type: none">• IP 1C-Manual hand pump.• IP 1C-Compact electrical airless diaphragm pump.• IP 1C-Pro electrical airless diaphragm pump.• Packers and connectors. See relevant TDS.
• health & safety	Elastopack 201 A-component is not classified. Elastopack 201 B-component is classified as harmful. All persons in contact with the materials should wear the appropriate protective clothing and gloves. Spills should be washed immediately with abundant quantities of clean water. For full information, consult the relevant Material Safety Data Sheet.

*All data mentioned on this technical data sheet are product descriptions. They are the result of general experience and experiments and don't take any specific application into account. No further demands may be derived from these data. The manufacturer has the privilege to implement technical changes, which result from new research concerning the material composition and form. To verify that you are holding the latest version of this technical Data Sheet, please visit www.deneef.eu.
De Neef Conchem • 26-07-2010-01.*